



COR-MET, INC.
12500 GRAND RIVER ROAD
BRIGHTON, MI 48116-8326
(810) 227-3251
800-848-2719
FAX: (810) 227-9266
www.cor-met.com

COR®FACE 164 MC

DESCRIPTION

COR™FACE 164 MC is a metal-cored, wear-resistant alloy designed to combat abrasion and corrosion. It is a nickel-chrome-boron-silicon matrix with 55 weight% tungsten carbide particles.

APPLICATIONS

164 MC is typically used for overlaying carbon, low-alloy, manganese, and stainless steels. The welded deposit is very corrosion resistant, which makes it suitable for use in the plastics industry. Other uses would include applications where toughness and wear resistance are required in or out of corrosive environments.

PROCEDURE

Hardfacing generally does not require any heat treatment. Preheat and post-heat according to the base metal requirements where necessary. Increased preheat and slow cooling virtually eliminate any cracking.

WELDING PARAMETERS

size	Volts	Amps	Shielding Gas/Flux
MC-G 1/16"	20-23	210-250	100%Ar or 75%Ar-25%CO ₂

MECHANICAL PROPERTIES

Hardness: Matrix: 38-42 Rc as-welded
WC Particles: 2600 Knoop (no Rc conversion available)

CLASSIFICATION

WC particles in a nickel-chrome-boron-silicon matrix